

Protective Coatings

EPOMARINE PUTTY 环氧腻子

PRODUCT DESCRIPTION

A putty based on epoxy resin, polyamide hardener.

产品简介

由环氧树脂、聚酰胺固化剂组成的环氧腻子

RECOMMENDED USE

As filling and leveling putty for concrete or cement surfaces.

用途

作为混凝土或水泥表面填孔、找平腻子使用。

FEATURES

Excellent scraping performance

产品特性

极好的刮涂施工性

Excellent burnishing performance

优异的打磨性 Quick dry 干燥迅速

Excellent adhesion 极好的附着性

PHYSICAL PROPERTIES

基本数据

Color Grey 颜色 灰色

Theoretical Coverage

 $2.50 Kg/m^2/1mm$

理论涂覆率

2.50 千克/平方米/1 毫米

Practical coverage depending on surface conditions, environment, applications, etc.

实际涂覆率与表面处理, 外界环境, 施工方法等多种因素有关。

APPLICATION

施工

Application Temperature

5℃-40℃

施工温度

Mixing Combine Base with Hardener, mix thoroughly with power agitator

混合 混合主剂与固化剂,使用动力工具搅拌均匀

Mixing RatioBase/Hardener=26/4.2 (by weight)混合比例主剂/固化剂=26/4.2 (质量比)Pot life5 $^{\circ}$ $^{$

Application MethodsTrowel施工方法抹途升

Thinner No Thinning No not thin

稀释剂 无需稀释





Can be sanded 5% 20% 30% 可打磨时间 36hrs 20hrs 16hrs

Applied substrateConcrete, cement适用底材混凝土,水泥

Typical topcoat Epomarine concrete finish

适用上涂 环氧水泥地面漆

STORAGE Store in dry, cool condition and away from sources of heat and ignition. Containers must be kept

贮存 tightly closed.

贮存于干燥阴凉的环境中,远离热源及火源。包装桶必须保持封闭。

Shelf life 12 months from date of production $(25^{\circ}C)$

贮存期限 自生产之日起 12 个月(25℃)

DISCLAIMER

提请注意

The information given on this sheet is to the best of our knowledge and accurate at the time of issuing. Since conditions of use are beyond the manufacturer's control, information contained herein is without warranty, implied or otherwise, and the suitability of the material for the use contemplated is the sole responsibility of the buyer. The information contained on this data sheet is subject to modification at any time due to our policy of modification and product development. Please check this date sheet is current prior to using the product.

本说明书所提供信息均为目前我方所掌握最全面正确的资料,鉴于产品使用条件非我方所 能控制,此中信息不含担保,即仅在选取产品上对买方负责。由于我公司产品及生产工艺 的不断发展,本说明书的内容也会随时进行更改,此中所有信息均以我方确认为主。产品 使用前,请确认所持说明书为最新版本。

www.kansai.com.cn

Issued Date 2011/6/27 发行日期 2011/6/27