

## EPOSEAL 60PS

## 环氧煤沥青漆 60PS

### PRODUCT DESCRIPTION

A high build polyamide epoxy bitumen coating

#### 产品简介

厚涂型聚酰胺固化环氧煤沥青涂料

### RECOMMENDED USE

As a primer can be used in steel structure at industrial severe corrosive environments including water ballast tanks, crude oil tanks, underground pipelines etc.

#### 用途

用于严重腐蚀环境下的钢结构表面，用于压载舱、原油舱、埋地管线等。

### FEATURES

Outstanding corrosion resistance

#### 产品特性

优良的防腐性能

Resistance to cathodic protection

耐阴极保护

Suitable for crude oil loading and sea water immersion

适于储存原油，可以承受海水浸泡

Excellent resistance to impacts and abrasions

极好的耐冲击和耐磨损性能

Excellent high-build applicability

极好的厚涂施工性

Excellent compatibility with bare steel substrates and shop-primed surfaces

同裸钢底材及车间底漆的配套性极佳

### PHYSICAL PROPERTIES

#### 基本数据

##### Color

Black and Brown

##### 颜色

黑色和棕色

##### Volume Solids

68%

##### 体积固体份

##### VOC

290g/L, accord with EU Dirrctive2004/42/EC, subcategory j

##### 挥发性有机化合物含量

290 克/升，符合欧盟溶剂排放指令 2004/42/EC，j 子类别

##### Flash Point

Greater than 25°C

##### 闪点

25°C 以上

##### Film thickness

Dry 100-250microns/coat      Wet : 147-368microns/coat

##### 涂装膜厚

干膜: 100-250 微米/道      湿膜: 147-368 微米/道

##### Theoretical Coverage

0.255kg/m<sup>2</sup>/125 microns

##### 理论涂覆率

0.255 千克/平方米/125 微米

Practical coverage depending on surface conditions, environment, applications, etc.

实际涂覆率与表面处理，外界环境，施工方法等多种因素有关。

### APPLICATION

#### 施工

##### Application Temperature

5°C-40°C

##### 施工温度

##### Mixing

Combine Base with Hardener, mix thoroughly with power agitator

##### 混合

混合主剂与固化剂，使用动力工具搅拌均匀

##### Mixing Ratio

Base/Hardener=9/1(by weight)

##### 混合比例

主剂/固化剂=9/1（质量比）

<b>Pot life</b>	10°C	20°C	30°C
混合使用期	14hrs	12hrs	8hrs

**Application Methods** Airless spray, air spray, brush and roller  
 施工方法 无气喷涂、空气喷涂、刷涂、滚涂

Airless spray 无气喷涂

Nozzle tip	喷嘴尺寸	0.43mm-0.53mm
Nozzle pressure	出口压力	≥10Mpa
Thinning ratio	稀释比率	0-5% by volume (体积比)

Brush/Roller 刷涂、滚涂

Thinning ratio	稀释比率	5-10% by volume (体积比)
----------------	------	-----------------------

**Thinner** Eposeal Thinner #30  
 稀释剂 环氧稀释剂#30

<b>Drying time &amp; Overcoating interval</b>	Temperature	温度	10°C	20°C	30°C
干燥时间&涂装间隔	Surface dry	指触干燥	3hrs	2hrs	1hr
	Touch dry	半硬干燥	36hrs	16hrs	12hrs
	Before flooding	耐浸干燥	10days	7days	5days
	Min. interval	最小涂装间隔	36hrs	24hrs	16hrs
	Max. interval	最大涂装间隔	7days	7days	7days

**Applied substrate** Bare steel  
 适用底材 裸钢

**STORAGE** Store in dry, cool condition and away from sources of heat and ignition. Containers must be kept tightly closed.  
 贮存

贮存于干燥阴凉的环境中，远离热源及火源。包装桶必须保持封闭。

**Shelf life** 12 months from date of production (25°C)  
 贮存期限 自生产之日起 12 个月 (25°C)

**DISCLAIMER** The information given on this sheet is to the best of our knowledge and accurate at the time of issuing. Since conditions of use are beyond the manufacturer's control, information contained herein is without warranty, implied or otherwise, and the suitability of the material for the use contemplated is the sole responsibility of the buyer. The information contained on this data sheet is subject to modification at any time due to our policy of modification and product development. Please check this data sheet is current prior to using the product.  
 提请注意

本说明书所提供信息均为目前我方所掌握最全面正确的资料,鉴于产品使用条件非我方所能控制, 此中信息不含担保, 即仅在选取产品上对买方负责。由于我公司产品及生产工艺的不断发展, 本说明书的内容也会随时进行更改, 此中所有信息均以我方确认为主。产品使用前, 请确认所持说明书为最新版本。

[www.kansai.com.cn](http://www.kansai.com.cn)

Issued Date 2011/06/27  
 发行日期 2011/06/27