

NU FORTE

特种环氧漆 NU FORTE

PRODUCT DESCRIPTION

A low VOC, high solids, two pack surface tolerant epoxy maintenance coating.

产品简介

是一种低 VOC 含量、高固体、双组份表面容忍型环氧涂料。

RECOMMENDED USE

For a variety surface including hand prepared rusty steel and other low requirement surface at environments of maintenance.

用途

在维修配套中用于手动工具处理的带锈底材或其他低表面处理要求的表面

FEATURES

Low VOC, High volume solids

产品特性

低 VOC 含量，高固体份

Good anti-corrosive performance

极好的防腐性能

Excellent surface-tolerant properties

极好的表面适应性能

Tough and strong films

漆膜坚韧

Good adhesion to damp surfaces

同潮湿表面也有良好的附着力

PHYSICAL PROPERTIES

基本数据

Color

Grey and Oxide Red

颜色

灰色和铁红色

Volume Solids

80%

体积固体份

VOC

210g/L, accord with EU Dirctrive2004/42/EC, subcategory j

挥发性有机化合物含量

210 克/升，符合欧盟溶剂排放指令 2004/42/EC, j 子类别

Flash Point

Greater than 24°C

闪点

24°C 以上

Film thickness

Dry 75-200microns/coat Wet :94-250microns/coat

涂装膜厚

干膜:75-200 微米/道 湿膜: 94-250 微米/道

Theoretical Coverage

0.227Kg/m²/125 microns

理论涂覆率

0.227 千克/平方米/125 微米

Practical coverage depending on surface conditions, environment, applications, etc.

实际涂覆率与表面处理，外界环境，施工方法等多种因素有关。

APPLICATION

施工

Application Temperature

5°C-40°C

施工温度

Mixing

Combine Base with Hardener, mix thoroughly with power agitator

混合

混合主剂与固化剂，使用动力工具搅拌均匀

Mixing Ratio

Base/Hardener=9/1(by weight)

混合比例

主剂/固化剂=9/1（质量比）

Pot life

10°C 20°C 30°C

混合使用期

8hrs 4hrs 2hrs

Application Methods

施工方法

Airless spray, air spray, brush and roller

无气喷涂、空气喷涂、刷涂、滚涂

Airless spray 无气喷涂

Nozzle tip	喷嘴尺寸	0.43mm-0.53mm
Nozzle pressure	出口压力	≥15Mpa
Thinning ratio	稀释比率	0-5% by volume (体积比)

Brush/Roller 刷涂、滚涂

Thinning ratio	稀释比率	5-10% by volume (体积比)
----------------	------	-----------------------

Thinner

稀释剂

Nu Forte Thinner

专用稀释剂

Drying time &

Overcoating interval

干燥时间&涂装间隔

Temperature	温度	10°C	20°C	30°C
Surface dry	指触干燥	8hrs	5hrs	3hrs
Touch dry	半硬干燥	30hrs	16hrs	12hrs
Min. interval	最小涂装间隔	30hrs	16hrs	12hrs
Max. interval	最大涂装间隔	7days	7days	7days

Typical undercoat

适用下涂

Bare steel, various of existing paints etc..

裸钢, 大部分旧漆膜等

Typical topcoat

适用上涂

RETAN 6000, or according to the coating system of Cosco Kansai.

聚氨酯面漆 6000, 或参考我司涂装配套

STORAGE

贮存

Store in dry, cool condition and away from sources of heat and ignition. Containers must be kept tightly closed.

贮存于干燥阴凉的环境中, 远离热源及火源。包装桶必须保持封闭。

Shelf life

贮存期限

12 months from date of production (25°C)

自生产之日起 12 个月 (25°C)

DISCLAIMER

提请注意

The information given on this sheet is to the best of our knowledge and accurate at the time of issuing. Since conditions of use are beyond the manufacturer's control, information contained herein is without warranty, implied or otherwise, and the suitability of the material for the use contemplated is the sole responsibility of the buyer. The information contained on this data sheet is subject to modification at any time due to our policy of modification and product development. Please check this date sheet is current prior to using the product.

本说明书所提供信息均为目前我方所掌握最全面正确的资料,鉴于产品使用条件非我方所能控制, 此中信息不含担保, 即仅在选取产品上对买方负责。由于我公司产品及生产工艺的不断发展, 本说明书的内容也会随时进行更改, 此中所有信息均以我方确认为主。产品使用前, 请确认所持说明书为最新版本。

www.kansai.com.cn

Issued Date 2011/6/27

发行日期 2011/6/27