

## RETAN 6000

## 聚氨酯 6000 面漆

<b>PRODUCT DESCRIPTION</b> 产品简介	A high gloss durable finish based on polyurethane for steel surfaces of heavy-duty. 用于重防腐金属表面的高光泽高性能聚氨酯面漆。			
<b>RECOMMENDED USE</b> 用途	As a finish can be used in new construction situations and as industrial maintenance finish for bridges and port machinery etc. 用于新建设施或作为维修保养面漆使用，用于桥梁、港口机械等重防腐设施。			
<b>COMPLIED STANDARDS</b> 符合标准	Complies with JT/T 722-2008, JT/T 695-2007, TB/T 1527-2004, JT/T 733-2008 符合公路桥梁钢结构防腐涂装技术条件 JT/T 722-2008，混凝土桥梁结构表面涂层防腐技术条件 JT/T 695-2007，铁路钢桥保护涂装 TB/T 1527-2004，港口机械钢结构表面防腐涂层技术条件 JT/T 733-2008			
<b>FEATURES</b> 产品特性	Outstanding weathering resistance and gloss retention 优秀的耐候性和保光性  Good adhesion to epoxy primers 同环氧涂料附着良好  Outstanding resistance to impact and abrasion 优秀的耐冲击和耐磨损性能			
<b>PHYSICAL PROPERTIES</b> 基本数据				
<b>Color</b> 颜色	White and Colors 白色及各色			
<b>Gloss</b> 光泽	High Gloss 高光			
<b>Volume Solids</b> 体积固体份	52%			
<b>VOC</b> 挥发性有机化合物含量	430g/L, accord with EU Dirrctive2004/42/EC, subcategory j 430g/L，符合欧盟溶剂排放指令 2004/42/EC，j 子类别			
<b>Flash Point</b> 闪点	Greater than 23℃ 23℃以上			
<b>Film thickness</b> 涂装膜厚	Dry 30-50microns/coat 干膜:30-50 微米/道		Wet : 58-96microns/coat 湿膜: 58-96 微米/道	
<b>Theoretical Coverage</b> 理论涂布率	0.091kg/m <sup>2</sup> /40 microns 0.091 千克/平方米/40 微米  Practical coverage depending on surface conditions, environment, applications, etc. 实际涂布率与表面处理，外界环境，施工方法等多种因素有关。			
<b>APPLICATION</b> 施工				
<b>Application Temperature</b> 施工温度	-5℃-40℃			
<b>Mixing</b> 混合	Combine Base with Hardener, mix thoroughly with power agitator 混合主剂与固化剂，使用动力工具搅拌均匀			
<b>Mixing Ratio</b> 混合比例	Base/Hardener=8/1(by weight) 主剂/固化剂=8/1（质量比）			
<b>Pot Life</b> 混合使用期	5℃ 8hrs	10℃ 6hrs	20℃ 5hrs	30℃ 3hrs

## Application Methods

施工方法

Airless spray, air spray, brush and roller

无气喷涂、空气喷涂、刷涂、滚涂

Airless spray 无气喷涂

Nozzle tip	喷嘴尺寸	0.33mm-0.43mm
Nozzle pressure	出口压力	≥10Mpa
Thinning ratio	稀释比率	10-20% by weight (重量比)

Brush/Roller 刷涂、滚涂

Thinning ratio	稀释比率	0-10% by weight (重量比)
----------------	------	-----------------------

## Thinner

稀释剂

Retan Thinner

聚氨酯稀释剂

## Drying time &

### Overcoating interval

干燥时间&涂装间隔

Temperature	温度	-5℃	0℃	10℃	20℃	30℃
Surface dry	指触干燥	4hrs	2hrs	1.5hrs	1hr	1hr
Touch dry	半硬干燥	24hrs	16hrs	12hrs	10hrs	6hrs
Min. interval	最小涂装间隔	30hrs	24hrs	20hrs	16hrs	12hrs
Max. interval	最大涂装间隔	-	-	-	-	-

## Typical undercoat

适用下涂

Universal EP-50, Universal MIO-50 or according to the coating systems of Cosco Kansai

Universal EP-50, Universal MIO-50 或参考我司推荐配套

## Typical topcoat

适用上涂

## STORAGE

贮存

Store in dry, cool condition and away from sources of heat and ignition. Containers must be kept tightly closed.

贮存于干燥阴凉的环境中，远离热源及火源。包装桶必须保持封闭。

## Shelf life

贮存期限

12 months from date of production (25℃)

自生产之日起 12 个月 (25℃)

## DISCLAIMER

提请注意

The information given on this sheet is to the best of our knowledge and accurate at the time of issuing. Since conditions of use are beyond the manufacturer's control, information contained herein is without warranty, implied or otherwise, and the suitability of the material for the use contemplated is the sole responsibility of the buyer. The information contained on this data sheet is subject to modification at any time due to our policy of modification and product development. Please check this data sheet is current prior to using the product.

本说明书所提供信息均为目前我方所掌握最全面正确的资料,鉴于产品使用条件非我方所能控制, 此中信息不含担保, 即仅在选取产品上对买方负责。由于我公司产品及生产工艺的不断发展, 本说明书的内容也会随时进行更改, 此中所有信息均以我方确认为主。产品使用前, 请确认所持说明书为最新版本。

[www.kansai.com.cn](http://www.kansai.com.cn)

Issued Date 2011/6/27

发行日期 2011/6/27